



Product Performance Values: Easy-Tilt Double Hung

Description	U-Value	SHGC	VLT	CR
Sun Clad USA Easy-Tilt Double Hung - Clear Glass , Double Glazed I.G. with 1/2" spacer				
Single Strength Glass, No Grilles	0.50	0.61	0.63	41
Sun Clad USA Easy-Tilt Double Hung - Sun Advantage 270 Low-E with Argon, Double Glazed I.G. with 1/2" spacer				
Single Strength Glass, No Grilles	0.33	0.24	0.48	54
Single Strength Glass, ClimaGuard SPF, No Grilles	0.32	0.24	0.47	54
Single Strength Glass, Tinted Glass, No Grilles	0.33	0.24	0.39	54
Double Strength Glass, No Grilles	0.33	0.24	0.48	54
Double Strength Glass, ClimaGuard SPF, No Grilles	0.33	0.24	0.47	54
Double Strength Glass, Tinted Glass, No Grilles	0.33	0.27	0.36	54
Double Strength Glass, Solar Cool Bronze, No Grilles	0.33	0.13	0.14	54
Single Strength Glass, Grilles Between the Glass	0.33	0.22	0.43	54
Single Strength Glass, ClimaGuard SPF, Grilles Between the Glass	0.32	0.22	0.42	52
Single Strength Glass, Tinted Glass, Grilles Between the Glass	0.33	0.22	0.35	54
Double Strength Glass, Grilles Between the Glass	0.33	0.22	0.43	54
Double Strength Glass, ClimaGuard SPF, Grilles Between the Glass	0.33	0.22	0.42	54
Double Strength Glass, Tinted Glass, Grilles Between the Glass	0.33	0.24	0.32	54
Double Strength Glass, Solar Cool Bronze, Grilles Between the Glass	0.33	0.12	0.12	54
Single Strength Glass, Simulated Divided Lite Grilles (<1)	0.33	0.22	0.43	54
Single Strength Glass, ClimaGuard SPF, Simulated Divided Lite Grilles (<1)	0.32	0.22	0.42	52
Single Strength Glass, Tinted Glass, Simulated Divided Lite Grilles (<1)	0.33	0.22	0.35	54
Double Strength Glass, Simulated Divided Lite Grilles (<1)	0.33	0.22	0.43	54
Double Strength Glass, ClimaGuard SPF, Simulated Divided Lite Grilles (<1)	0.33	0.22	0.42	54
Double Strength Glass, Tinted Glass, Simulated Divided Lite Grilles (<1)	0.33	0.24	0.32	54
Double Strength Glass, Solar Cool Bronze, Simulated Divided Lite Grilles (<1)	0.33	0.12	0.12	54
Single Strength Glass, Simulated Divided Lite Grilles (>=1)	0.33	0.20	0.38	54
Single Strength Glass, ClimaGuard SPF, Simulated Divided Lite Grilles (>=1)	0.32	0.20	0.37	52
Single Strength Glass, Tinted Glass, Simulated Divided Lite Grilles (>=1)	0.33	0.19	0.31	54
Double Strength Glass, Simulated Divided Lite Grilles (>=1)	0.33	0.20	0.38	54
Double Strength Glass, ClimaGuard SPF, Simulated Divided Lite Grilles (>=1)	0.33	0.19	0.37	54
Double Strength Glass, Tinted Glass, Simulated Divided Lite Grilles (>=1)	0.33	0.22	0.28	54
Double Strength Glass, Solar Cool Bronze, Simulated Divided Lite Grilles (>=1)	0.33	0.11	0.11	54
Sun Clad USA Easy-Tilt Double Hung - Sun Advantage 366 Low-E with Argon, Double Glazed I.G. with 1/2" spacer				
Single Strength Glass, No Grilles	0.33	0.21	0.42	54
Single Strength Glass, Dual Low-E, No Grilles	0.32	0.19	0.28	55
Single Strength Glass, ClimaGuard SPF, No Grilles	0.33	0.21	0.41	54
Single Strength Glass, Tinted Glass, No Grilles	0.33	0.21	0.34	54
Single Strength Glass, Grilles Between the Glass	0.34	0.19	0.37	54
Single Strength Glass, Dual Low-E, Grilles Between the Glass	0.33	0.17	0.25	55
Single Strength Glass, ClimaGuard SPF, Grilles Between the Glass	0.34	0.19	0.36	54
Single Strength Glass, Tinted Glass, Grilles Between the Glass	0.34	0.19	0.30	54
Sun Clad USA Easy-Tilt Double Hung - Sun Advantage 270 Plus with 4th surface Low-E, Double Glazed I.G. with 1/2" spacer				
Single Strength Glass, Dual Low-E, No Grilles	0.29	0.23	0.45	44
Double Strength Glass, Dual Low-E, No Grilles	0.29	0.23	0.44	43
Single Strength Glass, Dual Low-E, Grilles Between the Glass	0.29	0.21	0.40	44
Double Strength Glass, Dual Low-E, Grilles Between the Glass	0.29	0.21	0.39	43
Single Strength Glass, Dual Low-E, Simulated Divided Lite Grilles (<1)	0.29	0.21	0.40	44
Double Strength Glass, Dual Low-E, Simulated Divided Lite Grilles (<1)	0.29	0.21	0.39	43
Single Strength Glass, Dual Low-E, Simulated Divided Lite Grilles (>=1)	0.29	0.19	0.35	44
Double Strength Glass, Dual Low-E, Simulated Divided Lite Grilles (>=1)	0.29	0.19	0.35	43
<i>Note: All values listed are lab certified under specific conditions. Actual values of finished installed products may vary.</i>				