



Description	U-Value	SHGC	VLT	CR
Sun Clad USA Sidelite - Clear Glass , Double Glazed I.G. with 1/2" spacer				
Double Strength Glass, No Grilles				
Sun Clad USA Sidelite - Sun Advantage 270 Low-E with Argon, Double Glazed I.G. with 1/2" spacer				
Double Strength Glass, No Grilles	0.30	0.19	0.38	64
Double Strength Glass, ClimaGuard SPF, No Grilles	0.30	0.19	0.38	64
Double Strength Glass, Tinted Glass, No Grilles	0.30	0.19	0.35	64
Double Strength Glass, Solar Cool Bronze, No Grilles	0.30	0.11	0.11	64
Double Strength Glass, Grilles Between the Glass	0.31	0.17	0.34	64
Double Strength Glass, ClimaGuard SPF, Grilles Between the Glass	0.31	0.17	0.34	64
Double Strength Glass, Tinted Glass, Grilles Between the Glass	0.31	0.17	0.31	64
Double Strength Glass, Solar Cool Bronze, Grilles Between the Glass	0.31	0.10	0.10	64
Double Strength Glass, Simulated Divided Lite Grilles (<1)	0.31	0.17	0.34	64
Double Strength Glass, ClimaGuard SPF, Simulated Divided Lite Grilles (<1)	0.31	0.17	0.34	64
Double Strength Glass, Tinted Glass, Simulated Divided Lite Grilles (<1)	0.31	0.17	0.31	64
Double Strength Glass, Solar Cool Bronze, Simulated Divided Lite Grilles (<1)	0.31	0.10	0.10	64
Double Strength Glass, Simulated Divided Lite Grilles (>=1)	0.31	0.16	0.30	64
Double Strength Glass, ClimaGuard SPF, Simulated Divided Lite Grilles (>=1)	0.31	0.16	0.30	64
Double Strength Glass, Tinted Glass, Simulated Divided Lite Grilles (>=1)	0.31	0.16	0.28	64
Double Strength Glass, Solar Cool Bronze, Simulated Divided Lite Grilles (>=1)	0.31	0.09	0.09	64
Sun Clad USA Sidelite - Sun Advantage 270 Low-E with Argon, Triple Glazed I.G. with two 3/8" spacers				
Double Strength Glass, No Grilles	0.27	0.18	0.35	64
Double Strength Glass, ClimaGuard 63/31, No Grilles	0.23	0.16	0.27	64
Double Strength Glass, ClimaGuard SPF, No Grilles	0.27	0.18	0.35	64
Double Strength Glass, Solar Cool Bronze, No Grilles	0.27	0.10	0.10	64
Double Strength Glass, Dual Low-E, No Grilles	0.24	0.17	0.32	57
Double Strength Glass, Grilles Between the Glass	0.28	0.16	0.32	64
Double Strength Glass, ClimaGuard 63/31, Grilles Between the Glass	0.24	0.15	0.24	64
Double Strength Glass, Solar Cool Bronze, Grilles Between the Glass	0.28	0.09	0.09	64
Double Strength Glass, Dual Low-E, Grilles Between the Glass	0.25	0.15	0.29	56
Double Strength Glass, Simulated Divided Lite Grilles (<1)	0.28	0.16	0.32	64
Double Strength Glass, ClimaGuard 63/31, Simulated Divided Lite Grilles (<1)	0.24	0.15	0.24	64
Double Strength Glass, Solar Cool Bronze, Simulated Divided Lite Grilles (<1)	0.28	0.09	0.09	64
Double Strength Glass, Dual Low-E, Simulated Divided Lite Grilles (<1)	0.25	0.15	0.29	56
Double Strength Glass, Simulated Divided Lite Grilles (>=1)	0.28	0.15	0.28	64
Double Strength Glass, ClimaGuard 63/31, Simulated Divided Lite Grilles (>=1)	0.24	0.13	0.22	64
Double Strength Glass, Solar Cool Bronze, Simulated Divided Lite Grilles (>=1)	0.28	0.09	0.08	64
Double Strength Glass, Dual Low-E, Simulated Divided Lite Grilles (>=1)	0.25	0.14	0.25	56
Sun Clad USA Sidelite - Sun Advantage 366 Low-E with Argon, Double Glazed I.G. with 1/2" spacer				
Single Strength Glass, No Grilles	0.30	0.17	0.33	64
Single Strength Glass, ClimaGuard SPF, No Grilles	0.30	0.17	0.33	64
Single Strength Glass, Grilles Between the Glass	0.31	0.15	0.30	64
Sun Clad USA Sidelite - Sun Advantage 366 Low-E with Argon, Triple Glazed I.G. with two 3/8" spacers				
Single Strength Glass, ClimaGuard SPF, No Grilles	0.27	0.16	0.30	64
Sun Clad USA Sidelite - Sun Advantage 270 Plus with 4th surface Low-E, Double Glazed I.G. with 1/2" spacer				
Double Strength Glass, Dual Low-E, No Grilles	0.27	0.18	0.35	51
Double Strength Glass, Dual Low-E, Grilles Between the Glass	0.28	0.17	0.31	51
Double Strength Glass, Dual Low-E, Simulated Divided Lite Grilles (<1)	0.28	0.17	0.31	51
Double Strength Glass, Dual Low-E, Simulated Divided Lite Grilles (>=1)	0.28	0.15	0.28	51

Note: All values listed are lab certified under specific conditions. Actual values of finished installed products may vary.